

Qr Resin QR-1008

Polycarbonate
LyondellBasell Industries
Engineering Plastics

Product Description

Available with UV (V) or Release (R).

General

Features	• High Impact Resistance	
Appearance	• Colors Available	• Natural Color
Forms	• Pellets	
Processing Method	• Extrusion	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.20	1.20 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 Kg)	8.0 g/10 min	8.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	9000 psi	62.1 MPa	ASTM D638
Flexural Modulus	340000 psi	2340 MPa	ASTM D790
Flexural Strength (Yield)	14000 psi	96.5 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	14 ft·lb/in	750 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	280 °F	138 °C	
264 Psi (1.8 Mpa), Unannealed	270 °F	132 °C	



Qr Resin QR-1008

Polycarbonate
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	250 °F	121 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Drying Time, Maximum	4.0 hr	4.0 hr
Rear Temperature	540 to 580 °F	282 to 304 °C
Middle Temperature	560 to 600 °F	293 to 316 °C
Front Temperature	580 to 620 °F	304 to 327 °C
Nozzle Temperature	570 to 610 °F	299 to 321 °C
Processing (Melt) Temp	580 to 620 °F	304 to 327 °C
Mold Temperature	180 to 240 °F	82 to 116 °C

Notes

These are typical property values not to be construed as specification limits.

