

Diamaloy Engineered Alloys 808 C2 WW

Polycarbonate Alloy
LyondellBasell Industries
Engineering Plastics

General			
Agency Ratings	• EC 1907/2006 (REACH) • EU 2002/96/EC (WEEE) • FDA 21 CFR 174.105 • FDA 21 CFR 175.105(b)(3)(viii)	• FDA 21 CFR 176.170(c), Table 2, Cond. C • FDA 21 CFR 176.170(c), Table 2, Cond. D • FDA 21 CFR 176.170(c), Table 2, Cond. E • FDA 21 CFR 176.170(c), Table 2, Cond. F	• FDA 21 CFR 176.170(c), Table 2, Cond. G • FDA 21 CFR 177.1580
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.21	1.21 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹			ASTM D1238
200°C/5.0 Kg	3.0 g/10 min	3.0 g/10 min	
230°C/3.8 Kg	12 g/10 min	12 g/10 min	
300°C/1.2 Kg	78 g/10 min	78 g/10 min	
Water Absorption			ASTM D570
24 Hr, 73°F (23°C)	0.15 %	0.15 %	
Equilibrium, 73°F (23°C)	0.35 %	0.35 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ² (Yield)	8000 psi	55.2 MPa	ASTM D638
Flexural Modulus - Tangent ³	300000 psi	2070 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	2.0 ft·lb/in	110 J/m	
Reverse Notch Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	No Break	No Break	
Gardner Impact (73°F (23°C))	> 320 in·lb	> 36.2 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 Psi (1.8 Mpa), Unannealed, 0.125 In (3.18 Mm)	172 °F	77.8 °C	
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Light Transmittance	90.0 %	90.0 %	ASTM D1003
Haze	1.00 %	1.00 %	ASTM D1003

Notes

¹ Procedure A

² 2.0 in/min (51 mm/min)

³ 0.050 in/min (1.3 mm/min)

Notes

These are typical property values not to be construed as specification limits.

