

Ferro Pp TPP20AW01UL-WH

Polypropylene
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Talc, 20% Filler by Weight		
Additive	• Impact Modifier		
Features	• Impact Modified		
Appearance	• White		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.06	1.06 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	17 g/10 min	17 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	3900 psi	26.9 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	5.0 %	5.0 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	260000 psi	1790 MPa	
Tangent : 73°F (23°C)	310000 psi	2140 MPa	
Flexural Strength (73°F (23°C))	6400 psi	44.1 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.3 ft·lb/in	69 J/m	ASTM D256
Instrumented Dart Impact (73°F (23°C))	600 in·lb	67.8 J	ASTM D3763
Gardner Impact (73°F (23°C))	275 in·lb	31.1 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
RTI Elec	248 °F	120 °C	UL 746B
RTI Imp	248 °F	120 °C	UL 746B
RTI Str	248 °F	120 °C	UL 746B



Ferro Pp TPP20AW01UL-WH

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.

