

Ferro Pp TPP40AN86GY

Polypropylene
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Talc, 41% Filler by Weight		
Additive	• Impact Modifier		
Features	• Impact Modified		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.26	1.26 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	3.5 g/10 min	3.5 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	3800 psi	26.2 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	25 %	25 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	345000 psi	2380 MPa	
Tangent : 73°F (23°C)	408000 psi	2810 MPa	
Flexural Strength (73°F (23°C))	5850 psi	40.3 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.1 ft·lb/in	59 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	8.6 ft·lb/in	460 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	100 in·lb	11.3 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	246 °F	119 °C	
264 Psi (1.8 Mpa), Unannealed	164 °F	73.3 °C	



Ferro Pp TPP40AN86GY

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.

