

Ferro Pp TPP40AJ30BK

Polypropylene Homopolymer

LyondellBasell Industries

Engineering Plastics

Product Description

Meets/Exceeds Ford Engineering Specification WSK-M4D644-A.

Primary end use is for AC housings.

General

Filler / Reinforcement	• Talc, 37% Filler by Weight
Additive	• Heat Stabilizer
Features	• Heat Stabilized • Homopolymer
Automotive Specifications	• FORD WSK-M4D644-A • VISTEON VAM-PP01TF40-0001 Application 001
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.22 g/cm ³	1.22 g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	14 g/10 min	14 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress (Yield, 73°F (23°C))	3840 psi	26.5 MPa	ISO 527-2
Flexural Modulus	551000 psi	3800 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact Strength			ISO 180
-40°F (-40°C)	0.81 ft·lb/in ²	1.7 kJ/m ²	
73°F (23°C)	1.1 ft·lb/in ²	2.3 kJ/m ²	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	264 °F	129 °C	ISO 75-2/B
264 Psi (1.8 Mpa), Unannealed	183 °F	84.0 °C	ISO 75-2/A


Additional Information

Tensile/Izod Change, ISO 188, 1000 hours, 140°C: +3%/0%



Ferro Pp TPP40AJ30BK

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.

