

Gapex RPP20EA34NA

Polypropylene Homopolymer

LyondellBasell Industries

Engineering Plastics


General			
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• Chemically Coupled	• Heat Stabilized	• Homopolymer
Automotive Specifications	• ASTM D5857 PP114 G20	• CHRYSLER MS-DB-500 CPN3577 Color: Natural	
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.04	1.04 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	5.0 g/10 min	5.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	9900 psi	68.3 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	4.0 %	4.0 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	526000 psi	3630 MPa	
Tangent : 73°F (23°C)	549000 psi	3780 MPa	
Flexural Strength (73°F (23°C))	1400 psi	9.65 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.3 ft·lb/in	69 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	8.2 ft·lb/in	440 J/m	ASTM D4812
Gardner Impact	3.50 in·lb	0.395 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	310 °F	154 °C	
264 Psi (1.8 Mpa), Unannealed	290 °F	143 °C	



Gapex RPP20EA34NA

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 180 °F	71 to 82 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	430 to 460 °F	221 to 238 °C
Middle Temperature	440 to 470 °F	227 to 243 °C
Front Temperature	450 to 500 °F	232 to 260 °C
Nozzle Temperature	450 to 500 °F	232 to 260 °C
Processing (Melt) Temp	430 to 460 °F	221 to 238 °C
Mold Temperature	100 to 150 °F	38 to 66 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	20.0 to 50.0 psi	0.138 to 0.345 MPa
Cushion	0.200 to 0.500 in	5.08 to 12.7 mm

Notes

These are typical property values not to be construed as specification limits.

