

Gapex RPP20EU66GY

Polypropylene
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 21% Filler by Weight		
Additive	• Impact Modifier		
Features	• Chemically Coupled • Impact Modified		
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.05	1.05 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	19 g/10 min	19 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	8200 psi	56.5 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	4.0 %	4.0 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	543000 psi	3740 MPa	
Tangent : 73°F (23°C)	575000 psi	3960 MPa	
Flexural Strength (73°F (23°C))	12400 psi	85.5 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.0 ft·lb/in	53 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	6.3 ft·lb/in	340 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	2.50 in·lb	0.282 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	310 °F	154 °C	
264 Psi (1.8 Mpa), Unannealed	285 °F	141 °C	


Additional Information

Testing and measurements were performed at 73 +/-3°F and 50 +/-5% relative humidity unless otherwise noted.



Gapex RPP20EU66GY

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 180 °F	71 to 82 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	430 to 460 °F	221 to 238 °C
Middle Temperature	440 to 470 °F	227 to 243 °C
Front Temperature	450 to 500 °F	232 to 260 °C
Nozzle Temperature	450 to 500 °F	232 to 260 °C
Processing (Melt) Temp	430 to 460 °F	221 to 238 °C
Mold Temperature	100 to 150 °F	38 to 66 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	20.0 to 50.0 psi	0.138 to 0.345 MPa
Cushion	0.200 to 0.500 in	5.08 to 12.7 mm

Notes

These are typical property values not to be construed as specification limits.

