

Technical Data Sheet

Hifax BB 73G T 2065 (EBONY)

Polypropylene Compounds



Product Description

Hifax BB 73G T 2065 (EBONY) is a 22% talc filled PP copolymer, with good processability, very good impact/stiffness balance, good UV resistance and good scratch resistance. Product is available as a customized color matched, pellet form. This grade is delivered in 2065 color version.

Application	Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Impact Resistance; Good Stiffness; Good UV Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	1.07	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	2200	MPa	ISO 178
Tensile Stress at Yield	22	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	6.5	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	110	°C	ISO 75B-1, -2

