

Technical Data Sheet

Hifax CB 1160 G1 G74010

Polypropylene Compounds



Product Description

Hifax CB 1160 G1 is a talc filled PP copolymer, with medium flowability, high impact resistance and good stiffness. This grade is delivered in customer customized colors. This Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

| | |
|-------------------|---|
| Application | Bumpers; Exterior Trim |
| Market | Automotive |
| Processing Method | Injection Molding |
| Attribute | Good Stiffness; High Impact Resistance; Medium Flow |

| Typical Properties | Nominal Value | Units | Test Method |
|---|---------------|-------------------|---------------|
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 14 | g/10 min | ISO 1133-1 |
| Density, (23 °C) | 0.97 | g/cm ³ | ISO 1183-1/A |
| Mechanical | | | |
| Flexural Modulus, (23 °C, Tech. A) | 1400 | MPa | ISO 178/A1 |
| Flexural Strength, (23 °C, Tech. A) | 22 | MPa | ISO 178/A1 |
| Tensile Stress at Yield, (23 °C) | 18 | MPa | ISO 527-1, -2 |
| Impact | | | |
| Notched Izod Impact Strength | | | |
| (23 °C) | 45 | kJ/m ² | ISO 180/1A |
| (-30 °C) | 6.5 | kJ/m ² | ISO 180/1A |
| Thermal | | | |
| Vicat Softening Temperature, (B50) | 52 | °C | ISO 306 |
| Deflection Temperature Under Load, (1.80 MPa, Unannealed) | 50 | °C | ISO 75A-1, -2 |

Notes

These are typical property values not to be construed as specification limits.

