

Technical Data Sheet

Hifax CB 45G T 2003 (SC BLACK)



Polypropylene Compounds

Product Description

Hifax CB 45G T 2003 (SC BLACK) is a 30% talc filled PP copolymer, with a good balance of flowability, impact strength and stiffness. Product is available as non color matched, black, pellet form.

Application	Exterior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Impact Resistance; Good Stiffness; Good UV Resistance; Medium Flow

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	10	g/10 min	ISO 1133-1
Density, (23 °C)	1.13	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus	2400	MPa	ISO 178
Tensile Stress at Yield	20	MPa	ISO 527-1, -2
Tensile Strain at Break	40	%	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	14	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	113	°C	ISO 75B-1, -2

