

Technical Data Sheet

Hifax ETA3041 YGYA BLK



Polypropylene Compounds

Product Description

Hifax ETA3041 YGYA BLK medium melt flow, 170 MPa flexural modulus, thermoplastic elastomeric olefin (TEO) resin has a good balance of flexibility and durability. It is typically used for a wide variety of molded-in color automotive exterior components.

Application Automotive Parts

Market Automotive

Processing Method Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	10	g/10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	170	MPa	ISO 178
Tensile Stress at Yield	7	MPa	ISO 527-1, -2
Additional Information			
Mold Shrinkage			ISO 294-4

Please contact LyondellBasell for shrinkage recommendations.

