

Technical Data Sheet

Hifax EYC 361P G13063

Polypropylene Compounds



Product Description

Hifax EYC 361P G13063 is a 9% talc filled PP copolymer, with high melt flow rate and good impact resistance. Product is available as a customized color matched, pellet form. This grade is delivered in G13063 color version.

Application	Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Impact Resistance; High Flow

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	28	g/10 min	ISO 1133-1
Density, (23 °C)	0.95	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1250	MPa	ISO 178/A1
Tensile Strength, (23 °C)	19	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	50	kJ/m ²	ISO 180/1A
(-30 °C)	7	kJ/m ²	ISO 180/1A

