

Technical Data Sheet

Hifax TRC 298P C11287

Polypropylene Compounds



Product Description

Hifax TRC 298P is a 20% talc filled PP copolymer, with high impact resistance, good processability, improved surface appearance, good scratch resistance and low CLTE (Coefficient of Linear Thermal Expansion). This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

Application	Automotive Parts; Exterior Automotive Applications; Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Dimensional Stability; Good Processability; High Impact Resistance; Pleasing Surface Appearance; Scratch Resistant; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	23	g/10 min	ISO 1133-1
Density, (23 °C)	1.05	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1400	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	15	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	35	kJ/m ²	ISO 180/1A
(0 °C)	25	kJ/m ²	ISO 180/1A

