

Technical Data Sheet

Hifax TRC 495P G13076

Polypropylene Compounds



Product Description

Hifax TRC 495P G13076 is a 16% talc filled PP copolymer, with superior impact/stiffness balance, excellent flowability, good processability and good UV resistance. The product is also available as a customized color matched, pellet form. This grade is delivered in G13076 color version.

Application	Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Processability; High Flow; High Impact Resistance; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ISO 1133-1
Density, (23 °C)	1	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1700	MPa	ISO 178/A1

