

Technical Data Sheet

Hifax TRS 260P C11319

Polypropylene Compounds



Product Description

Hifax TRS 260P C11319 is an unfilled PP copolymer, with very good processability and medium impact/stiffness balance. Product is available as a customized color matched, pellet form. This grade is delivered in C11319 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

Application	Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Excellent Processability

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	21	g/10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	600	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	16.5	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	55	kJ/m ²	ISO 179-1/1eA
(-40 °C)	7	kJ/m ²	ISO 179-1/1eA
Notched Izod Impact Strength			
(23 °C)	50	kJ/m ²	ISO 180/1A
(-40 °C)	8	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	64	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.

