

# Hifax TRC 779XHS

## **Compounded Polyolefin**

#### **Product Description**

Hifax TRC 779XHS high melt flow, medium high flexural modulus, paintable, mineral-filled thermoplastic elastomeric olefin (TEO) resin has an excellent balance of properties and processability. It was designed for use in multiple automotive exterior applications.

## **Product Characteristics**

Test Method used ISO

Processing Methods Injection Molding

**Typical Customer Applications** Exterior Applications

Typical Properties	Method	Value	Unit
Physical			
Density (Method A)	ISO 1183	0.98	g/cm³
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	25	g/10 min
Mechanical			
Flexural modulus (23 °C)	ISO 178	1500	MPa
Tensile stress at yield	ISO 527	17	MPa
Additional Information			
Mold shrinkage	ISO 294-4		
Note: Please contact LyondellBasell for shrinka	age recommendations	i.	

### **Notes**

Typical properties; not to be construed as specifications.



