

Technical Data Sheet

Hifax TYC 337X BLACK

Polypropylene Compounds



Product Description

Hifax TYC 337X is a 15% talc filled PP copolymer, with very high melt flow rate and good impact resistance. Product is available as a standard black.

This product is also available in other colors, new colors can be developed depending on customer requirements.

Application	Bumpers
Market	Automotive
Processing Method	Injection Molding
Attribute	High Flow

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	25	g/10 min	ISO 1133-1
Density, (23 °C)	1.02	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1350	MPa	ISO 178/A1
Tensile Stress at Yield	16	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C, Type 1, Notch A)	40	kJ/m ²	ISO 180/1A
(-30 °C, Type 1, Notch A)	5	kJ/m ²	ISO 180/1A
Thermal			
Heat Deflection Temperature B, (0.45 MPa, Unannealed)	82	°C	ISO 75B-1, -2

Notes

These are typical property values not to be construed as specification limits.

