

## Technical Data Sheet

### Hifax TYC 2149P S82589



Polypropylene Compounds

#### Product Description

Hifax TYC 2149P S82589 is a 12% talc filled PP copolymer, with excellent impact/stiffness balance, good flowability, very good surface appearance, very good UV resistance and excellent processability. Formula is improved to offer better aspect, especially on tiger stripes. Advanced technologies allowed for a significant reduction of mineral filler which contributed to the reduction of final part weight. Please contact lyondellbasell for shrinkage recommendations. The product is available in different color matched, pellet form. This grade is delivered in S82589 color version.

<b>Application</b>	Bumpers; Exterior Automotive Applications
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Flow; Good Processability; Good UV Resistance; Low Density

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	25	g/10 min	ISO 1133-1
Density, (23 °C)	0.99	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1500	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	17	MPa	ISO 527-1, -2
Tensile Strain at Break, (23 °C)	130	%	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C)	29	kJ/m <sup>2</sup>	ISO 179-1/1eA
(-30 °C)	3.5	kJ/m <sup>2</sup>	ISO 179-1/1eA
<b>Thermal</b>			
Vicat Softening Temperature, (A50)	125	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	90	°C	ISO 75B-1, -2

