

Technical Data Sheet

Hifax TYC 258X E2 BLACK

Polypropylene Compounds



Product Description

Hifax TYC 258X E2 BLACK is a 30% talc filled PP copolymer, with excellent flowability, low CLTE (Coefficient of Linear Thermal Expansion), very good processability and low UV resistance. Product is available in black color, pellet form.

Application	Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	High Stiffness; Low Shrinkage; Paintable

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	27	g/10 min	ISO 1133-1
Density, (23 °C)	1.14	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1800	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	17	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	20	kJ/m ²	ISO 179-1/1eA
(-30 °C)	3	kJ/m ²	ISO 179-1/1eA
Thermal			
Vicat Softening Temperature, (A50)	117	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	94	°C	ISO 75B-1, -2

