

Technical Data Sheet

Hifax TYC 2459P E C11287



Polypropylene Compounds

Product Description

Hifax TYC 2459P E C11287 is a 20% talc filled PP copolymer, with very low shrinkage, high flowability, good impact/stiffness balance and low CLTE (Coefficient of Linear Thermal Expansion). This grade is delivered in customer customized colors.

This product is also available in other colors, new colors can be developed depending on customer requirements.

Application	Automotive Parts; Exterior Automotive Applications; Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Dimensional Stability; Good Processability; High Impact Resistance; Pleasing Surface Appearance; Scratch Resistant; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	27	g/10 min	ISO 1133-1
Density, (23 °C)	1.05	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2100	MPa	ISO 178/A1
Tensile Strain at Break, (23 °C)	40	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	25	kJ/m ²	ISO 179-1/1eA
(-30 °C)	3.5	kJ/m ²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	110	°C	ISO 75B-1, -2

