

Technical Data Sheet

Hostacom M4 W01 100000

Polypropylene Compounds



Product Description

Hostacom M4 W01 100000 is a 40% talc filled PP homopolymer, with high melt flow rate. Product is available as a customized color matched, pellet form. This grade is delivered in Black color version.

Application	Underhood
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	28	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/2.16 kg)	28	cm ³ /10 min	ISO 1133-1
Density, (23 °C)	1.21	g/cm ³	ISO 1183-1/A
Mechanical			
Tensile Modulus, (23 °C)	3700	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C)	30	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	2.5	kJ/m ²	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	20	kJ/m ²	ISO 179-1/1eU
Thermal			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	85	°C	ISO 75A-1, -2

