

Technical Data Sheet

Hostacom M4 U05 102943

Polypropylene Compounds



Product Description

Hostacom M4 U05 102943 is a 40% talc filled PP homopolymer, with high flowability, high stiffness, low fogging and low odour. Product is available as a customized color matched, pellet form. This grade is delivered in 102943 color version.

Application	Automotive Parts
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	10	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/2.16 kg)	10	cm ³ /10 min	ISO 1133-1
Density, (23 °C)	1.21	g/cm ³	ISO 1183-1/A
Mechanical			
Tensile Modulus, (23 °C)	4300	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C)	32	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	2.5	kJ/m ²	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	25	kJ/m ²	ISO 179-1/1eU
Thermal			
Vicat Softening Temperature, (B50)	100	°C	ISO 306
Deflection Temperature Under Load			
(0.45 MPa, Unannealed)	130	°C	ISO 75B-1, -2
(1.80 MPa, Unannealed)	80	°C	ISO 75A-1, -2

