

Technical Data Sheet

Hostacom PC072-3M WHITE

Polypropylene Compounds



Product Description

Hostacom PC072-3M WHITE is a glass fiber reinforced PP homopolymer with low melt flow rate.

Application	White Goods
Market	Electrical / Electronics
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	2	g/10 min	ISO 1133-1
Density, (23 °C)	1.14	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	5400	MPa	ISO 178/A1
Tensile Modulus, (23 °C)	6400	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C)	85	MPa	ISO 527-1, -2
Tensile Strain at Yield, (23 °C)	3.5	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	9.5	kJ/m ²	ISO 179-1/1eA
(-20 °C)	6	kJ/m ²	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	40	kJ/m ²	ISO 179-1/1eU
Thermal			
Vicat Softening Temperature, (B50)	130	°C	ISO 306
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	130	°C	ISO 75A-1, -2

