

Technical Data Sheet

Hostacom PPN 1034 12

Polypropylene Compounds



Product Description

Hostacom PPN 1034 12 is an unfilled PP copolymer with medium melt flow rate and good low temperature impact resistance. The product is also available as a customized color matched, pellet form. This grade is delivered in BLACK color version.

Application	Automotive Parts; Underhood
Market	Automotive
Processing Method	Injection Molding
Attribute	Low Temperature Impact Resistance; Medium Flow

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/5.0 kg)	13	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/5.0 kg)	15	cm ³ /10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm ³	ISO 1183-1/A
Mechanical			
Tensile Modulus, (23 °C)	1050	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C)	24	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	50	kJ/m ²	ISO 179-1/1eA
Charpy Impact Strength - Unnotched			
(23 °C)	No Break		ISO 179-1/1eU
(0 °C)	No Break		ISO 179-1/1eU
Thermal			
Vicat Softening Temperature, (B50)	68	°C	ISO 306
Deflection Temperature Under Load			
(0.45 MPa, Unannealed)	80	°C	ISO 75B-1, -2
(1.80 MPa, Unannealed)	55	°C	ISO 75A-1, -2

Notes

These are typical property values not to be construed as specification limits.

