

Technical Data Sheet

Hostacom PPN 4160

Polypropylene Compounds



Product Description

Hostacom PPN 4160 is an unfilled PP homopolymer with low melt flow rate.
Product is UL listed.

Processing Method Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	2.5	g/10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1500	MPa	ISO 178/A1
Tensile Modulus, (23 °C)	1450	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C)	36	MPa	ISO 527-1, -2
Tensile Strain at Yield, (23 °C)	8	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	4.5	kJ/m²	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	No Break		ISO 179-1/1eU
Thermal			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	55	°C	ISO 75A-1, -2

