

Technical Data Sheet

Hostacom PPN 1060 12

Polypropylene Compounds



Product Description

Hostacom PPN 1060 12 is an unfilled PP homopolymer, with low melt flow and high stiffness. This grade is delivered in black color version.

Application	Underhood
Market	Automotive
Processing Method	Injection Molding
Attribute	Low Flow

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/5.0 kg)	7	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/5.0 kg)	10	cm ³ /10 min	ISO 1133-1
Density, (23 °C)	0.90	g/cm ³	ISO 1183-1/A
Mechanical			
Tensile Modulus, (23 °C)	1450	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C)	30	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	4.5	kJ/m ²	ISO 179-1/1eA
Charpy Impact Strength - Unnotched			
(23 °C)	45	kJ/m ²	ISO 179-1/1eU
(0 °C)	22	kJ/m ²	ISO 179-1/1eU
Thermal			
Deflection Temperature Under Load			
(0.45 MPa, Unannealed)	90	°C	ISO 75B-1, -2
(1.80 MPa, Unannealed)	55	°C	ISO 75A-1, -2

Notes

These are typical property values not to be construed as specification limits.

