

Technical Data Sheet

Hostacom T20C557 C1 C15974



Polypropylene Compounds

Product Description

Hostacom T20C557 C1 C15974 is a talc filled PP copolymer, with high melt flow rate and good impact/stiffness balance. Product is available as a customized color matched, pellet form. This grade is delivered in 3211 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements

This product is also available in other colors, new colors can be developed depending on customer requirements.

Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	25	g/10 min	ISO 1133-1
Density, (23 °C)	1.04	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2100	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	20	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	5	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	105	°C	ISO 75B-1, -2

