Technical Data Sheet

Hostacom TKC 2007N C12710



Polypropylene Compounds

Product Description

Hostacom TKC 2007N C12710 is a 5% talc filled PP copolymer, with low density, excellent blooming resistance at elevated temperatures, very good impact/stiffness balance, very good mouldability and excellent scratch resistance. Advanced technologies allowed for a significant reduction of mineral fillercontent which contributed to the reduction of final part weight. Please contact LyondellBasell for shrinkage recommendations. This product is also available in other colors, new colors can be developed depending on customer requirements.

Application Automotive Parts; Interior Trims

Market Automotive

Processing Method Injection Molding

Attribute Good Moldability; Low Density; Non Blooming; Scratch Resistant

| | Nominal | | |
|---|---------|----------|---------------|
| Typical Properties | Value | Units | Test Method |
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 16 | g/10 min | ISO 1133-1 |
| Density, (23 °C) | 0.93 | g/cm³ | ISO 1183-1/A |
| Mechanical | | | |
| Flexural Modulus, (23 °C, Tech. A) | 1650 | MPa | ISO 178/A1 |
| Tensile Stress at Yield, (23 °C) | 20 | MPa | ISO 527-1, -2 |
| Tensile Strain at Yield, (23 °C) | 4.8 | % | ISO 527-1, -2 |
| Impact | | | |
| Charpy Impact Strength - Notched | | | |
| (23 °C) | 35 | kJ/m² | ISO 179-1/1eA |
| (-30 °C) | 4.8 | kJ/m² | ISO 179-1/1eA |
| Thermal | | | |
| Vicat Softening Temperature, (A50) | 136 | °C | ISO 306 |
| Deflection Temperature Under Load, (1.80 MPa, Unannealed) | 56 | °C | ISO 75A-1, -2 |

Notes

These are typical property values not to be construed as specification limits.



