

Technical Data Sheet

Hostacom TKC 2007N G82765



Polypropylene Compounds

Product Description

Hostacom TKC 2007N G82765 is a 5% talc filled PP copolymer, with low density, excellent blooming resistance at elevated temperatures, very good impact/stiffness balance, very good mouldability and excellent scratch resistance. Advanced technologies allowed for a significant reduction of mineral filler content which contributed to the reduction of final part weight. Please contact LyondellBasell for shrinkage recommendations. This product is also available in other colors, new colors can be developed depending on customer requirements.

Application	Automotive Parts; Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Moldability; Low Density; Non Blooming; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	16	g/10 min	ISO 1133-1
Density, (23 °C)	0.93	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1650	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	20	MPa	ISO 527-1, -2
Tensile Strain at Yield, (23 °C)	4.8	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	35	kJ/m ²	ISO 179-1/1eA
(-30 °C)	4.8	kJ/m ²	ISO 179-1/1eA
Thermal			
Vicat Softening Temperature, (A50)	136	°C	ISO 306
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	56	°C	ISO 75A-1, -2

Notes

These are typical property values not to be construed as specification limits.

