

Technical Data Sheet

Hostacom TRC 103P C12990

Polypropylene Compounds



Product Description

Hostacom TRC 103P C12990 is a 15% talc filled PP copolymer, with high impact resistance. The product is also available as a customized color matched, pellet form. This grade is delivered in C12990 color version

Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Fast Cycle (Production); Good Dimensional Stability; Good Processability; Good UV Resistance; High Flow; High Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	23	g/10 min	ISO 1133-1
Density, (23 °C)	1	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1500	MPa	ISO 178/A1
Tensile Strength, (23 °C)	20	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	42	kJ/m ²	ISO 180/1A
(-30 °C)	5.3	kJ/m ²	ISO 180/1A
Thermal			
Deflection Temperature Under Load			
(0.45 MPa, Unannealed)	95	°C	ISO 75B-1, -2
(1.80 MPa, Unannealed)	54	°C	ISO 75A-1, -2

Notes

These are typical property values not to be construed as specification limits.

