

Technical Data Sheet

Hostacom TKC 420N C2 C15207

Polypropylene Compounds



Product Description

Hostacom TKC 420N C2 C15207 is a 10% talc filled PP copolymer, with good flowability, excellent impact/stiffness balance, very good scratch resistance and blooming resistance at elevated temperatures. Advanced technologies allowed for a significant reduction of mineral filler content which contributed to the reduction of final part weight. Product is available as a customized color matched, pellet form. This grade is delivered in C15207 color version

Application	Automotive Parts; Interior Trims
Market	Automotive
Attribute	Good Moldability; Non Blooming; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	17	g/10 min	ISO 1133-1
Density, (23 °C)	0.97	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1800	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	23	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	25	kJ/m ²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	55	°C	ISO 75B-1, -2

