

Technical Data Sheet

Hostacom TRC 1193N E C12360



Polypropylene Compounds

Product Description

Hostacom TRC 1193N E is an UV stabilised mineral filled polypropylene copolymer for injection moulding. It combines a very good flowability with high stiffness/ very good impact properties and excellent scratch resistance.

The grade has been specifically designed for moulding of large complex interior trim parts that requires good dimensional stability.

Application	Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	High Impact Resistance; High Stiffness

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ISO 1133-1
Density, (23 °C)	0.99	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1900	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	19	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Notch A)	50	kJ/m ²	ISO 179-1/1eA
(-40 °C)	3.5	kJ/m ²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	54	°C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.

