

## Technical Data Sheet

### Hostacom TRC 333N NA MOCCA

Polypropylene Compounds



#### Product Description

Hostacom TRC 333N NA MOCCA is a high flow thermoplastic olefinic elastomer (TPO) with excellent scratch resistance, very low stress whitening and low emissions and good stiffness/impact balance. It is typically used for interior trim applications.

Application	Automotive Parts; Interior Automotive Applications
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Impact Resistance; Good Stiffness; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	17	g/10 min	ASTM D1238
Density, (23 °C)	1.05	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Flexural Modulus	1900	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	25	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength, (23 °C)	30	kJ/m <sup>2</sup>	ISO 180
<b>Additional Information</b>			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			

#### Notes

These are typical property values not to be construed as specification limits.

