

Technical Data Sheet

Hostacom TRC 399N G14008



Polypropylene Compounds

Product Description

Hostacom TRC 399N G14008 is a 14% talc filled PP copolymer, with high melt flow, excellent impact/stiffness balance and very good surface appearance. Product is available as a customized color matched, pellet form. This grade is delivered in G14008 color version.

Application	Instrument Panels
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Flow; Good Processability

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	23	g/10 min	ISO 1133-1
Density, (23 °C)	1	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1800	MPa	ISO 178/A1
Impact			
Notched Izod Impact Strength			
(23 °C)	35	kJ/m ²	ISO 180/1A
(-30 °C)	5	kJ/m ²	ISO 180/1A

Notes

These are typical property values not to be construed as specification limits.

