## **Technical Data Sheet**

## Hostacom TRC 411N R G71260



Polypropylene Compounds

## **Product Description**

*Hostacom* TRC 411N R G71260 is a 20% talc filled PP copolymer compound, with high flowability, good impact/stiffness balance and excellent scratch resistance, offering low odour and low emissions performances.

This polypropylene compound is produced locally in Russia.

This product is also available in other colors, new colors can be developed depending on customer requirements.

**Application** Automotive Parts; Interior Automotive Applications

Market Automotive

Processing Method Injection Molding

Attribute Ductile; Good Abrasion Resistance; Good Color Stability; Good Processability; Good

Stiffness; Good Surface Finish; High Flow; High Impact Resistance; Low Temperature

Impact Resistance; Low to No Odor; Low VOC Emission; Pleasing Surface

Appearance; Scratch Resistant; UV Resistant

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	19	g/10 min	ISO 1133-1
Density, (23 °C)	1.04	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1800	MPa	ISO 178/A1
Impact			
Charpy Impact Strength - Notched, (23 °C)	25	kJ/m²	ISO 179-1/1eA
Thermal			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	90	°C	ISO 75B-1, -2

## **Notes**

These are typical property values not to be construed as specification limits.



