

## Technical Data Sheet

### Hostacom X M1 T02 C3 C15335



Polypropylene Compounds

#### Product Description

Hostacom X M1 T02 C3 C15335 is a 15% talc filled elastomer modified PP, with excellent impact/stiffness balance and very good processability, low gloss performance, The product is available in different color matched, pellet form. This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected. This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

<b>Application</b>	Automotive Parts; Instrument Panels; Interior Automotive Applications
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Processability; Good Stiffness; High Impact Resistance; Low Gloss; Medium Flow; Scratch Resistant; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density, (23 °C)	1.01	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1600	MPa	ISO 178/A1
Tensile Strength	17	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	35	kJ/m <sup>2</sup>	ISO 180/1A
(-30 °C)	5.5	kJ/m <sup>2</sup>	ISO 180/1A

#### Notes

These are typical property values not to be construed as specification limits.

