

Technical Data Sheet

Hostacom XBR 169 G C12306

Polypropylene Compounds



Product Description

Hostacom XBR 169 G C12306 is a 15% talc filled PP copolymer, with good processability and surface appearance, excellent impact/stiffness balance and good scratch resistance. It has been designed using the latest advancements in resin synthesis and compounding technology, reduction of mineral filler contributes to reduction of final part weight. Product is available as a customized color matched, pellet form. This grade is delivered in C12306 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

| | |
|-------------------|------------------------|
| Application | Instrument Panels |
| Market | Automotive |
| Processing Method | Injection Molding |
| Attribute | Good Impact Resistance |

| Typical Properties | Nominal Value | Units | Test Method |
|---|---------------|-------------------|---------------|
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 15 | g/10 min | ISO 1133-1 |
| Density, (23 °C) | 1.02 | g/cm ³ | ISO 1183-1/A |
| Mechanical | | | |
| Flexural Modulus, (23 °C, Tech. A) | 1650 | MPa | ISO 178/A1 |
| Tensile Stress at Yield, (23 °C) | 17 | MPa | ISO 527-1, -2 |
| Impact | | | |
| Notched Izod Impact Strength | | | |
| (23 °C) | 30 | kJ/m ² | ISO 180/1A |
| (-30 °C) | 4 | kJ/m ² | ISO 180/1A |
| Thermal | | | |
| Deflection Temperature Under Load, (0.45 MPa, Unannealed) | 100 | °C | ISO 75B-1, -2 |

Notes

These are typical property values not to be construed as specification limits.

