

Technical Data Sheet
Lucent PP CPP-110
Polypropylene Homopolymer
Engineering Plastics



Product Description

10% Calcium Carbonate Filled, Homopolymer Polypropylene

Melt Flow Adjustable for Application
Colors Available
Add "U" for UV Stabilized
Add "H" for Heat Stabilized

General

Filler / Reinforcement	• Calcium Carbonate, 10% Filler by Weight		
Features	• Homopolymer		
Appearance	• Clear/Transparent	• Colors Available	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.980	0.978 g/cm³	ASTM D792
Molding Shrinkage - Flow (0.125 in (3.18 mm))	0.014 in/in	1.4 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	4400 psi	30.3 MPa	ASTM D638
Tensile Elongation (Break)	> 10 %	> 10 %	ASTM D638
Flexural Modulus	240000 psi	1650 MPa	ASTM D790
Flexural Strength	6800 psi	46.9 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 in (3.18 mm))	0.80 ft·lb/in	43 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed	140 °F	60.0 °C	

Notes

These are typical property values not to be construed as specification limits.

