

Technical Data Sheet
Lucent PP CPP-130
Polypropylene Homopolymer
Engineering Plastics



Product Description

30% Calcium Carbonate Filled, Homopolymer Polypropylene

- Melt Flow Adjustable for Application
- Colors Available
- Add "U" for UV Stabilized
- Add "H" for Heat Stabilized

General

Filler / Reinforcement	• Calcium Carbonate, 30% Filler by Weight
Features	• Homopolymer
Appearance	• Colors Available

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.14	1.14 g/cm³	ASTM D792
Molding Shrinkage - Flow (0.125 in (3.18 mm))	0.012 in/in	1.2 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	3800 psi	26.2 MPa	ASTM D638
Tensile Elongation (Break)	> 10 %	> 10 %	ASTM D638
Flexural Modulus	350000 psi	2410 MPa	ASTM D790
Flexural Strength	6300 psi	43.4 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 in (3.18 mm))	0.80 ft·lb/in	43 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed	155 °F	68.3 °C	

Notes

These are typical property values not to be construed as specification limits.

