

Technical Data Sheet
Lucent PP GPP-240
Polypropylene
Engineering Plastics



Product Description

40% Glass Fiber Reinforced, Chemically Coupled, Impact Modified Polypropylene

Melt Flow Adjustable for Application
Colors Available
Add "U" for UV Stabilized
Add "H" for Heat Stabilized

General

Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight
Additive	• Impact Modifier
Features	• Chemically Coupled • Impact Modified
Appearance	• Colors Available

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.24	1.24 g/cm³	ASTM D792
Molding Shrinkage - Flow (0.125 in (3.18 mm))	3.0E-3 in/in	0.30 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	12500 psi	86.2 MPa	ASTM D638
Tensile Elongation (Break)	3.0 %	3.0 %	ASTM D638
Flexural Modulus	900000 psi	6210 MPa	ASTM D790
Flexural Strength	17500 psi	121 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 in (3.18 mm))	2.2 ft·lb/in	120 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	280 °F	138 °C	ASTM D648

Notes

These are typical property values not to be construed as specification limits.

