

Matrixx 12N4003

Polypropylene
LyondellBasell Industries
Engineering Plastics

General			
Additive	• Flame Retardant		
Features	• Flame Retardant	• Low Blooming	
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.940	0.938 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	8.0 g/10 min	8.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	3400 psi	23.4 MPa	ASTM D638
Flexural Modulus - Tangent	145000 psi	1000 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	3.0 ft·lb/in	160 J/m	ASTM D256
Gardner Impact	170 in·lb	19.2 J	ASTM D5420
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	185 °F	85.0 °C	ASTM D648
RTI Str	239 °F	115 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	V-2	V-2	UL 94

Notes

These are typical property values not to be construed as specification limits.

