

Matrixx 14N6020

Polypropylene
LyondellBasell Industries
Engineering Plastics

General		
Additive	• Flame Retardant	
Features	• Flame Retardant	• Low Blooming
Forms	• Pellets	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.990	0.988 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	18 g/10 min	18 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	5000 psi	34.5 MPa	ASTM D638
Flexural Modulus	210000 psi	1450 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.50 ft·lb/in	27 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	205 °F	96.1 °C	ASTM D648
RTI Elec	149 °F	65.0 °C	UL 746B
RTI Imp	149 °F	65.0 °C	UL 746B
RTI Str	149 °F	65.0 °C	UL 746B
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating (0.06 In (1.5 Mm))	V-0	V-0	UL 94

Additional Information

The value listed as Mold Shrinkage, ASTM D955, was tested in accordance with Matrixx test methods.

Notes

These are typical property values not to be construed as specification limits.

