

Technical Data Sheet
Matrixx 15S3302
Polypropylene
Engineering Plastics



General			
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Flame Retardant		
Features	• Flame Retardant		
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.47	1.47 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0 g/10 min	4.0 g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in (3.18 mm))	1.0E-3 to 3.0E-3 in/in	0.10 to 0.30 %	Internal Method
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	11500 psi	79.3 MPa	ASTM D638
Flexural Modulus - Tangent	980000 psi	6760 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	2.0 ft·lb/in	110 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	315 °F	157 °C	
264 psi (1.8 MPa), Unannealed	295 °F	146 °C	
RTI Str	200 °F	93.3 °C	UL 746
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.06 in (1.5 mm)	V-1	V-1	
0.12 in (3.0 mm)	• V-0	• V-0	
	• 5VA	• 5VA	

Notes

These are typical property values not to be construed as specification limits.

