

Matrixx FPP2B10CC

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General		
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight	
Features	• Good Stiffness	• Homopolymer
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Melt Mass-Flow Rate (MFR) (230°c/2.16 Kg)	5.0 to 10 g/10 min	5.0 to 10 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 74°f (23°c))	6500 psi	44.8 MPa	ASTM D638
Flexural Modulus - Tangent	300000 psi	2070 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact 73°f (23°c), 0.125 In (3.18 Mm)	0.80 ft-lb/in	43 J/m	ASTM D256



Matrixx FPP2B10CC

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature - Desiccant Dryer	160 °F	71 °C
Drying Time - Desiccant Dryer	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	390 to 470 °F	199 to 243 °C
Middle Temperature	390 to 470 °F	199 to 243 °C
Front Temperature	390 to 470 °F	199 to 243 °C
Processing (Melt) Temp	390 to 470 °F	199 to 243 °C
Mold Temperature	60 to 150 °F	16 to 66 °C
Injection Rate	Moderate	Moderate
Back Pressure ¹	< 50.0 psi	< 0.345 MPa
Screw Speed	50 to 150 rpm	50 to 150 rpm
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

Injection Notes
Drying not normally required. As needed for aesthetics only.

