

Technical Data Sheet

Hostacom G2 N02 100000

Polypropylene Compounds



Product Description

Hostacom G2 N02 100000 is a 20% glass fiber reinforced PP homopolymer, with high stiffness. This grade is delivered in black color version.

Application	Underhood
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/5.0 kg)	5.2	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/5.0 kg)	6	cm³/10 min	ISO 1133-1
Density, (23 °C)	1.05	g/cm³	ISO 1183-1/A
Mechanical			
Tensile Modulus, (23 °C)	4500	MPa	ISO 527-1, -2
Tensile Stress at Break, (23 °C)	72	MPa	ISO 527-1, -2
Tensile Strain at Break, (23 °C)	3.5	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C)	10	kJ/m²	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	40	kJ/m²	ISO 179-1/1eU
Thermal			
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	130	°C	ISO 75A-1, -2

