

Hostacom HBS826C

Polypropylene, Impact Copolymer

Product Description

Hostacom HBS826C fractional melt flow, medium flexural modulus, UV-stabilized, extrusion grade polypropylene copolymer has a good balance of strength and processability.

Product Characteristics

Test Method used	ISO
Processing Methods	Extrusion Pipe Sheet and Semi Finished Products
Features	Copolymer, Low Flow , Good Melt Strength , Good Processability, High Strength
Typical Customer Applications	Panels & Profiles

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	0.7	g/10 min
Density	ISO 1183	0.91	g/cm³
Mechanical			
Flexural modulus	ISO 178	1100	MPa
Tensile stress at yield	ISO 527	25	MPa
Tensile Elongation at Break	ISO 8986-2	500	%
Impact			
Notched izod impact strength (23 °C)	ISO 180	70	kJ/m²
Additional Information			
Mold shrinkage	ISO 294-4		
Note: Please contact LyondellBasell for shrinkage recommendations.			

Notes

Typical properties; not to be construed as specifications.

