

Technical Data Sheet

Hostacom HKG 247T BLACK



Polypropylene Compounds

Product Description

Hostacom HKG 247T BLACK is a 40% glass fiber reinforced PP homopolymer, with very high stiffness, low melt flow rate, low creep under load at elevated temperatures and very high thermal resistance. The product is available in black color, pellet form.

Application	Automotive Parts
Market	Automotive
Processing Method	Injection Molding
Attribute	High Stiffness

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	4	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/2.16 kg)	4	cm ³ /10 min	ISO 1133-1
Density, (23 °C)	1.22	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	9800	MPa	ISO 178/A1
Tensile Modulus, (23 °C)	9000	MPa	ISO 527-1, -2
Tensile Stress at Break, (23 °C)	108	MPa	ISO 527-1, -2
Tensile Strain at Break, (23 °C)	2.5	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	11	kJ/m ²	ISO 179-1/1eA
(0 °C)	10	kJ/m ²	ISO 179-1/1eA
(-30 °C)	10	kJ/m ²	ISO 179-1/1eA
Charpy Impact Strength - Unnotched, (23 °C)	45	kJ/m ²	ISO 179-1/1eU
Thermal			
Vicat Softening Temperature, (B50)	142	°C	ISO 306
Deflection Temperature Under Load, (1.80 MPa, Unannealed)	150	°C	ISO 75A-1, -2

Notes

These are typical property values not to be construed as specification limits.

