

Polyfort POLYFORT FPP 1902HU-3380

Polypropylene
LyondellBasell Industries
Engineering Plastics

Product Description

POLYFORT FPP 1902HU-3380 is an 11% Talc-Filled, UV Stabilized Polypropylene

General


Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Talc, 11% Filler by Weight
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.990 g/cm ³	0.990 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)	29 g/10 min	29 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress (Yield)	4260 psi	29.4 MPa	ISO 527-2
Tensile Strain (Break)	18 %	18 %	ISO 527-2/50
Flexural Modulus - Tangent	256000 psi	1760 MPa	ISO 178
Flexural Stress	6800 psi	46.9 MPa	ISO 178
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed	253 °F	123 °C	ISO 75-2/A
Additional Information	Nominal Value (English)	Nominal Value (SI)	Test Method
Filler Content	11 %	11 %	ASTM D5630



Polyfort POLYFORT FPP 1902HU-3380

Polypropylene
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Moderate-Fast	Moderate-Fast

Injection Notes

Polypropylene is not hygroscopic and generally does not require drying. As a good practice and to avoid residual humidity from transport or storage conditions, we recommend drying the material.
Ensure good mold venting
Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Notes

These are typical property values not to be construed as specification limits.

