

Polyfort PP 3761U-3120

Polypropylene Homopolymer

LyondellBasell Industries

Engineering Plastics

Product Description

Polyfort PP 3761U-3120 is an Unfilled Polypropylene Homopolymer

General


Appearance	• Colors Available
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.902	0.900 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	12 g/10 min	12 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	5020 psi	34.6 MPa	ASTM D638
Tensile Elongation ² (Break)	43 %	43 %	ASTM D638
Flexural Modulus ³	258000 psi	1780 MPa	ASTM D790
Flexural Strength (Yield)	7150 psi	49.3 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.1 ft·lb/in	57 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	230 °F	110 °C	ASTM D648



Polyfort PP 3761U-3120

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Moderate-Fast	Moderate-Fast

Injection Notes

Polypropylene is not hygroscopic and generally does not require drying. As a good practice and to avoid residual humidity from transport or storage conditions, we recommend drying the material.
Ensure good mold venting
Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.



Polyfort PP 3761U-3120

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

Notes

¹ 20 in/min (500 mm/min)

² 0.0 in/min (0.0 mm/min)

³ 0.051 in/min (1.3 mm/min)

Notes

These are typical property values not to be construed as specification limits.

