

POLYFORT® PPH M8 E LE U

Polypropylene Homopolymer
Engineering Plastics

Product Description

8% talc filled PP-Homopolymer UV stabilized, low heat conductivity

General

Filler / Reinforcement	• Talc, 8.0% Filler by Weight	
Features	• Low Fogging	• UV Stabilized
Processing Method	• Extrusion	• Injection Molding
Resin ID (ISO 1043)	• PP-T	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.950 g/cm ³	0.950 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	3.00 cm ³ /10min	3.00 cm ³ /10min	ISO 1133
Molding Shrinkage	0.90 to 1.3 %	0.90 to 1.3 %	ISO 294-4
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	305000 psi	2100 MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	5080 psi	35.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	7.5 %	7.5 %	ISO 527-2/1A/50
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	1.2 ft·lb/in ²	2.5 kJ/m ²	
73°F (23°C)	2.9 ft·lb/in ²	6.0 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	11 ft·lb/in ²	24 kJ/m ²	
73°F (23°C)	No Break	No Break	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			ISO 75-2/Bf
66 psi (0.45 MPa), Unannealed	221 °F	105 °C	
Vicat Softening Temperature	309 °F	154 °C	ISO 306/A50
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	


Additional Information

1.) Not for use in medical or pharmaceutical applications



POLYFORT® PPH M8 E LE U

Polypropylene Homopolymer
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Suggested Max Regrind	20 %	20 %
Processing (Melt) Temp	446 to 518 °F	230 to 270 °C
Mold Temperature	104 to 158 °F	40 to 70 °C

Injection Notes

Drying normally not necessary.
Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Notes

These are typical property values not to be construed as specification limits.

